

Our Ref: SW/RM

10 March 2020

Report 360242

Page 1 of 2

SMD Contracts Limited
Unit F2 Pittman Way
Fulwood
Preston
PR2 9ZD

Contact: Tracey O'Gara; Emma Lockwood; Sarah West

DATE RECEIVED : 2 MAR 2020
 FABRIC SUPPLIER : SMD
 QUALITY/REFERENCE : BELGRAVIA
 REPUTED FIBRE CONTENT : 100% POLYESTER
 FABRIC DESCRIPTION : WOVEN
 COLOUR/DESIGN : ANTIQUE GOLD
 END USE : CONTACTED UPHOLSTERY
 PERFORMANCE STANDARD : BS2543:2004 & BSEN 14465:2003 + A1:2006

REPORT SUMMARY

Tests	Method	Pass	Fail	Requirement
Determination of Sulphur Staining	BS 3424-19:1989 22A Determination of Sulphur Staining			No requirement
Abrasion of upholstery	Abrasion Resistance BS EN ISO 12947-2: 1998 / BS EN 14465: 2003 Annex A	Pass		Level A suitable for Any End Use



S. WISEMAN
LABORATORY DIRECTOR

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



118 Lupton Avenue Leeds LS9 6ED
 Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk
 Registered No. 2899980 VAT No. 613 4310 86

10 March 2020

Report 360242

Page 2 of 2

COLOUR FASTNESS TO:

BS 3424-19:1989 22A Determination of Sulphur Staining *

Immediately after test Grade 4 Temporary Staining

After 24 Hours Grade 4-5 Stained

Requirement:

PHYSICAL

Abrasion Resistance BS EN ISO 12947-2: 1998 / BS EN 14465: 2003 Annex A ~

12 kPa load.

Number of rubs to breakdown:	
Head 1 100,000+	
Head 2 100,000+	
Head 3 100,000+	
Head 4 100,000+	
Shade change after 3,000 rubs:	4-5

Requirement:

Level A suitable for Any
End Use

*Tests indicated * are non-UKAS accredited.*

Tests indicated § are within the bounds of the flexible scope of accreditation operated by the laboratory.

