

Smd Contracts Ltd
Mrs. Victoria Dyson
Pittman Way, Fulwood
PR2 9ZD PRESTON, LANCASHIRE
Verenigd Koninkrijk



Your notice of	Your reference	Date
11-08-2014		29-08-2014

Analysis Report 14.03865.01

Required tests :

NF P 92-507 (2004)

Identification number	Information given by the client	Date of receipt
T1412985	BURGHLEY CLARET FR VINYL	11-08-2014

Gina Créelle

Order responsible

This report runs to 2 pages and may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.

The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

VAT BE 0459.218.289

Fin. Acc. 210-0472965-45

IBAN BE44 2100 4729 6545

CENTEXBEL-GENT
Technologiepark 7
BE-9052 Zwijnaarde
Tel. + 32 9 220 41 51 • Fax + 32 9 220 49 55
gent@centexbel.be

CENTEXBEL-VERVIERS
Avenue du Parc 38
BE-4650 Herve (Chaineux)
Tel. + 32 87 32 24 30 Fax + 32 87 34 05 18
chaineux@centexbel.be

Reference: T1412985 - BURGLEY CLARET FR VINYL

Classification of materials according to their reaction to fire - "Electric burner"

Date of ending the test 28-08-2014
 Standard used NF P 92-503 (1995)
 Product standard NF P 92-507 (2004)

Deviation from the standard -

Sample thickness ≤ 5 mm

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
 Minimum 7 days or until constant mass is achieved

Only the front side has been tested

	Length		Width	
	Face A	Face B	Face A	Face B
Hole formation	no	no	no	no
Max. afterflame time (s)	1	1	0	1
Afterglow	no	no	no	no
Afterglow with propagation in area > 25 cm	no	no	no	no
Damaged length (cm)	21.0	21.5	21.0	22.0
Damaged width (cm) in area >45 cm	0	0	0	0
Flaming molten droplets	no	no	no	no
Non-flaming molten droplets	no	no	no	no
Flaming debris	no	no	no	no
Non-flaming debris	no	no	no	no
Average damaged length (cm)	21.5			
Average damaged width (cm) in area > 45 cm	0			

Classification M1