

Our Ref: SW/LS/BR

05 September 2018

**Report 327453**

**Page 1 of 2**

SMD Contracts Limited  
Unit F2 Pittman Way  
Fulwood  
Preston  
PR2 9ZD

Contact: Katie Hamblett

---

DATE RECEIVED	:	23 AUGUST 2018
QUALITY/REFERENCE	:	CLARA
REPUTED FIBRE CONTENT	:	NOT GIVEN
FABRIC DESCRIPTION	:	WOVEN
COLOUR/DESIGN	:	CLARA
BATCH NUMBER	:	CONTRACTS 97

---

REQUEST: Flammability in accordance with IMO 2010 FTP CODE ANNEX 1 PART 7

---

COMMENTS: See report

---



**S. WISEMAN**  
**LABORATORY DIRECTOR**



**L. SHERIDAN**  
**LABORATORY MANAGER**

This report shall not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.

\*This test has been sub-contracted

Our Ref: SW/LS/BR

05 September 2018

**Report 327453**

**Page 2 of 2**

**Flammability in accordance with IMO 2010 FTP CODE ANNEX 1 PART 8**

**Conditioning**

A minimum of 24 hours at 65±5% Relative Humidity, 20±5°C

**Report**

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a configuration.

Face	Warp direction					Weft direction				
Specimen number	1	2	3	4	5	1	2	3	4	5
Flame reached and edge (✓ or X)	X	X	X	X	X	X	X	X	X	X
Hole reach an edge (✓ or X)	X	X	X	X	X	X	X	X	X	X
Surface flash (✓ or X)	X	X	X	X	X	X	X	X	X	X
Duration of flaming (s)	0	0	0	0	0	0	0	0	0	0
Length of char (mm)	76	70	72	62	69	64	59	71	51	72
Ignition of Cotton wool (Y/N)	N	N	N	N	N	N	N	N	N	N

Mean Char Length Warp= 70mm Weft= 63mm

Back	Warp direction					Weft direction				
Specimen number	1	2	3	4	5	1	2	3	4	5
Flame reached and edge (✓ or X)	X	X	X	X	X	X	X	X	X	X
Hole reach an edge (✓ or X)	X	X	X	X	X	X	X	X	X	X
Surface flash (✓ or X)	X	X	X	X	X	X	X	X	X	X
Duration of flaming (s)	0	0	0	0	0	0	0	0	0	0
Length of char (mm)	84	82	103	66	75	78	88	66	73	63
Ignition of Cotton wool (Y/N)	N	N	N	N	N	N	N	N	N	N

Mean Char Length Warp= 82mm Weft= 74mm

**Comments**

On the basis of the tests carried out this sample of fabric meets the performance criteria for curtains and drapes as specified in Clause 3 of IMO 2010 FTP CODE ANNEX 1 PART 7.