

Our Ref: SW/PN/GL 22 July 2015

<u>Report 258146</u> <u>Page 1 of 2</u>

SMD Conracts Limited Unit F2 Pitman Way Fulwood Preston

PR2 9ZD Contact: Victoria Dyson

DATE RECEIVED : 16 JULY 2015 QUALITY/REFERENCE : Q8099 HARRIS

REPUTED FIBRE CONTENT : POLY WITH ANTIBAC/CRIB 5/

FLUOROCARBON COATING

FABRIC DESCRITION : WOVEN COLOUR/DESIGN : GRAPHITE END USE : UPHOLSTERY

REQUEST: IMO Fire Test Procedures 2010: Part 8 Test for upholstered furniture

COMMENTS: The sample submitted is classified as meeting the flammability performance

requirements of Part 8 of the IMO 2010 FTP Code.

S. WISEMAN LABORATORY MANAGER

P. NEESAM HEAD OF FLAMMABILITY

This report shall not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.



Our Ref: SW/PN/GL 22 July 2015

<u>Page 2 of 2</u>

IMO Fire Test Procedures 2010: Part 8 Test for upholstered furniture

Procedure

The specimen of Fabric, Ref: Q: 8099 Harris was tested in the "as received" condition using standard non-flame retardent polyurethane foam filling material of approximate density of 20-22 kg/m³. The tests were carried out after the specimens had been conditioned for 72 hours at indoor ambient conditions followed by 16 hours in the standard atmosphere of (23 ± 2) °C and (50 ± 5) % relative humidity.

Tests were carried out using ignition source '0' (smouldering cigarette) and '1' (match equivalent propane flame). All tests were performed in duplicate.

Note: Commercial grade propane gas (approx. 90% purity) was used instead of the 95% pure propane gas specified in the test method.

Requirements

Ignition source 0	No flaming or progressive smouldering within one hour of the placement of the cigarettes.
Ignition source 1	All flaming and progressive smouldering to cease within 120 seconds of the removal of the burner tube.

In addition if progressive smouldering is found on dismantling the test rig then the sample fails the requirements of the above standard.

Results

The following test results relate only to the behaviour of the test specimen of a product under the particular conditions of test stated; they are not intended to be the sole criterion for assessing the fire hazard of the product in use.

Ignition source	Duration of flaming, s	Progressive Smouldering	Assessment of ignition
0	0	No	Pass
0	0	No	Pass
1	15	No	Pass
1	6	No	Pass

Comments

The sample submitted is classified as meeting the flammability performance requirements of Part 8 of the IMO 2010 FTP Code.