

Results

Description of sample

Sample number: **2019-1410-02** Received: 24.10.2019
Business: POLYMER Type: QC

Identification: PVC (=Falcone FF)
Main Component: 73% PVC
Minor Component: 22% CO + 5% PU
Appearance: Brown
Field of Application: Furniture

Sanitized Products: Sanitized® TPL 27-42
Declared quantity: 0.13%
Finishing Process(es): Mixed in PVC paste before coating

Finishing Parameter(s): T max: 190°C

Remark: Production sample

Test results of the SANITIZED-laboratory

Qualitative test for determination of the antimycotic effectiveness:				
Method	Test point	Growth	Halo in mm	Evaluation
AATCC 30-2017 Part III	Penicillium funiculosum ATCC 36839	None	-	Good effect

Results

Description of sample

Sample number: **2019-0785-02** Received: 17.06.2019
Business: POLYMER Type: LIC

Identification: PVC (Falcone FF)
Main Component: 73% PVC
Minor Component: 22% CO + 5% PU
Appearance: Dark Brown (540g/m2)
Field of Application: Furniture

Sanitized Products: Sanitized® TPL 27-42
Declared quantity: 0.13%
Finishing Process(es): Mixed in PVC paste before coating

Finishing Parameter(s): T max: 190°C

Remark: Production sample
Quality control for lic. 5149.08

Test results of the SANITIZED-laboratory

Qualitative test for determination of the antibacterial effectiveness:				
Method	Test point	Growth	Halo in mm	Evaluation
AATCC 147:2016	Staphylococcus aureus (MRSA) ATCC 33592	None	1 mm	Good effect