

**TEST REPORT NO: 149694**

Date: 03 January 2019

**SMD CONTRACTS LTD  
UNIT F2, PITTMAN WAY, FULWOOD  
PRESTON  
LANCASHIRE  
PR29ZD  
UNITED KINGDOM**

The following sample(s) was/were submitted and identified by/on behalf of the client as:

Retailer	Not Specified
Description of article	HOUNDS TOOTH
Retailer style number	BEIGE/ORANGE
Retailer Standard Number	UNKNOWN
Order No./ Buyer	K.HAMBLETT
Quality/Fibre Composition	UNKNOWN
Date Sample(s) Received:	11 December 2018

Tests	Pass	Fail	Remarks
Resistance to Pilling (Modified Martindale)			See results
Abrasion Resistance			See results

Signature

For and on behalf of  
SGS United Kingdom Ltd

All samples are conditioned to ISO 139 where conditioning is required (unless otherwise stated)

This document is issued by the Company under its General Conditions of Service accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only

**Customer:** SMD CONTRACTS LTD      **Test Report No:** 149694

## Test Results


### Resistance to Pilling (BS EN ISO 12945-2:2000) Modified Martindale (As received)

Cycles	Rating
125	4-5 No significant change
500	4-5 No significant change
1000	4-5 No significant change
2000	4 Slight fuzzing

### Abrasion Resistance (BS EN ISO 12947-1 & 2:1999) 12kPa @ End Point

<b>Head 2 Breakdown</b>	80,000 Rubs
<b>Head 3 Breakdown</b>	80,000 Rubs
<b>Head 4 Breakdown</b>	80,000 Rubs
<b>Average</b>	80,000 Rubs
<b>Shade Change</b>	3,000 Rubs Grade 4-5

End of Report



This document is issued by the Company under its General Conditions of Service accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only