

QUALITY TEST RESULTS

Demand Detail No: 26705/001	Project Name:
Design Name : GOPA BASIC/SEATTLE	Control Date : 25.10.2021
Finishing : KA01	Explanation :

Test Name	Test Value	Test Result	Test Method
Width cm	>-%1,5	141	ISO 22198
Fabric Weight gr/m*2	-%5 +%10	536	ISO 3801
Tensile strength-Weft (N)	A:>=600 N,B:>=400,C:>=350 N,D:>=250 N	1470	ISO 13934-1
Tensile strength-Warp (N)	A:>=600 N,B:>=400,C:>=350 N,D:>=250 N	888	ISO 13934-1
Tear strength-Weft (N)	A:>=40N,B:>=30N,C:>=25N,D:>=20N,E:>=15N	>25	ISO 13937-2
Tear strength-Warp (N)	A:>=40N,B:>=30N,C:>=25N,D:>=20N,E:>=15N	176	ISO 13937-2
Seam slippage-Weft (mm)	A:<=4mm,B:<=6mm,C:<=8mm	3-4	ISO 13936-2
Seam slippage-Warp (mm)	A:<=4mm,B:<=6mm,C:<=8mm	1-2	ISO 13936-2
Resistance to pilling-2000c	A:>=4-5,B:4,C:3-4,D:3	4/5	ISO 12945-2
Colour change at 5000c	A:>=4-5,B:4,C:3-4,D:3	4/5	ISO 12947-2/ISO 12947-4
2nd Thread Break-Mrtndl	A:>=35000,B:12000-30000,C:4000-10000	>50.000	ISO 12947-2
Colour Fastness to Rubb.dry	A:>=4-5,B:4,C:3-4	4/5	ISO 105-X12
Colour Fastness to Rubb.wet	A:>=3-4,B:3,C:2-3	4/5	ISO 105-X12
Colour Fastness to Light	A:>=6,B:>=5,C:>=4	.	TS EN ISO 105-B2
Flammability	OK/NOK	.	BS5852 EN 1021-1
Wyzenbeek		>50.000	ASTM D4157-13
Dimensional changeafter washing (warp)	>+-2,5	.	EN ISO 6330
Dimensional changeafter washing (weft)	>+-2,5	.	EN ISO 6330